#### **Product Information**

## Specialty Lubricants

#### **FEATURES**

- · High load carrying capacity
- Suitable for long-term lubrication
- · Good oxidation resistance
- Emergency running properties, i.e. in the case of mixed friction providing of wear protection by solid lubricants and EP additives
- Good protection against scaring (false Brinelling)
- Good water washout resistance
- Good corrosion protection
- Good protection against fretting corrosion

#### COMPOSITION

- Mineral oil
- Lithium soap
- · Solid lubricants
- EP additive
- · Corrosion inhibitor

### MOLYKOTE<sup>®</sup> BR 2 plus High Performance Grease

# High performance grease with solid lubricants for metal/metal combinations involving slow to fast movements, particularly with medium to high loads

#### APPLICATION

• Used successfully on roller bearings, plain bearings, sliding guides, roller guides, ball-and-socket joints, splined shafts and threaded spindles.

#### **TYPICAL PROPERTIES**

Specification writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales representative prior to writing specifications on this product.

Standard	Test	Unit	Result		
	Color		Black		
	Consistency, density, viscosity				
DIN 51 818	NLGI consistency class		2		
ISO 2137	Worked penetration	mm/10	265-295		
ISO 2811	Density at 20°C	g/ml	0.89		
DIN 51 562	Base oil viscosity at 40°C1	mm²/s	114		
	Temperature				
	Service temperature	°C	-30 to +130, +150 for short periods		
ISO 2176	Drop point	°C	>=175		
ASTM- D-1478-80	Low temperature torque test at -20°C				
	Initial break-away torque	Nm	151		
	Torque after 20 minutes running time	Nm	59		
	Load-carrying capacity, wear protection, service life				
	Four-ball tester (VKA)				
DIN 51 350 pt.4	Weld load	Ν	3600		
DIN 51 350 pt.5	Wear scar under 800N load	mm	0.8		
	Almen-Wieland machine				
	OK load	Ν	15,500		
	Frictional force with OK load	Ν	3150		
DIN 51821-02-A	FAG rolling element bearing tester equipment, FE 9, 4500/6000-130, F‡}	h	40		
	Speed				
	DN value <sup>2</sup>	mm/min	450,000		
	Resistance				
DIN 51 808	Oxidation resistance, pressure drop 100h, $99^\circ\text{C}$	bar	0.1		
	Corrosion protection				
DIN 51 802	SKF-Emcor method		0		

#### **TYPICAL PROPERTIES (continued)**

Standard	Test	Unit	Result	
	Oil separation - evaporation			
DIN 51 817	Oil separation, 7 days, 40°C	%	3.8	

1. Calculated viscosity value of base oil mixture.

2. DN values are calculated approximations and will vary widely with temperature, load and bearing type.

#### HOW TO USE

#### How to apply

Clean points of contact. Apply in same way as lubricating greases, using brush, spatula, grease-gun or automatic lubricating device. Suitable for delivery by central lubricating system.

#### HANDLING PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE FROM YOUR LOCAL DOW CORNING SALES REPRESENTATIVE.

## USABLE LIFE AND STORAGE

When stored at or below 20°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

#### PACKAGING

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest Dow Corning sales office or Dow Corning distributor.

#### LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

#### HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Health, Environment and Regulatory Affairs specialists available in each area.

For further information, please consult your local Dow Corning representative.

#### WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. Dow Corning specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless Dow Corning provides you with a specific, duly signed endorsement of fitness for use, Dow Corning disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent.