

# Black-Seal Special Silicone



## Extremely resistant against oil and grease

WEICON Black-Seal is black, high-temperature-resistant (+280°C/+536°F), free of solvents, strong, oil-resistant, grease-resistant, pressure-resistant, resistant to ageing and extremely elastic (breaking elongation of approx. 500%). It is suitable for bonding and sealing in applications where particularly high oil and grease resistance is required. The product can be used on gearbox, valve and casing covers, oil sumps, water pumps, gears and axles, flanges, tanks and containers, and in many other areas.

### Technical Data

Base	1-C. polysiloxane (acetate)	
Colour	black	
Solid content	96 %	
Cure type	moisture-curing	
Standfestigkeit_Ablauf	ASTM D 2202	1.0 mm
Density	1,06 g/cm³	
Curing condition	from +5°C to +40°C and 30% to 95% rel. air air humidity	
Processing temperature	+5°C to +35°C	
Curing speed	in the first 24 h	2 -3 mm
Skin-over time	7 min.	
Gap bridging up to max.	5 mm	
Max. sealing joint width	25 mm	
Tensile strength	ISO 37 / S3A	2 N/mm²
Tensile strength of the pure adhesive and sealant	ISO 37	2 N/mm²
Medium lap shear strength (DIN EN 1465/ASTM D 1002)	0,7 N/mm²	
Elongation at break (tensile)	DIN 53504/ASTM D412	500 %
Elongation at break	ISO 37, S3A	470 %
Tear resistance	DIN 53515 / ASTM D 1002	4 kN/m
Elongation at 100 %	ISO 37 S3A	0,7 N/mm²
Movement absorption max.	15 %	
Volume change	DIN 52451	-9 %
Hardness (Shore A)	DIN ISO 7619	30±5
Temperature resistance	-60 °C to briefly +280 °C (approx. 2 h) +300 °C	
Thermal conductivity	0,3 W/m·K	
Resistance	2,5 x 10 <sup>15</sup> Ω·m	
Dielectric strength	21,0 kV/mm	
Building material class	DIN 4102	B 2
Shelf life	12 mon.	
<b>Zulassungen / Richtlinien</b>		
IMPA Code	815248/85/86	
ISSA Code	75.634.24/25/26	

### Surface pre-treatment

Surfaces must be clean and free of grease. Many surface soilings, such as oil, grease, dust and dirt can be removed with WEICON

Surface Cleaner. For heavily soiled metal surfaces, we recommend Cleaner Spray S; for removing old colour residues or adhesive

residues, WEICON Sealant and Adhesive Remover is ideal. Most materials can be bonded to and among each other. For certain materials or special requirements, we recommend the use of a

bonding agent (primer). Mechanical surface pre-treatment e.g. by grinding or sanding can also improve the adhesion considerably.

#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871 info@weicon.it

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr

# Black-Seal Special Silicone

## Processing

Application methods: Cartridge gun for 310 ml cartridges, compressed air gun, we recommend a version with piston rod (WEICON Compressed Air Cartridge Gun), automatic dosing systems. Squeeze out by hand, close tube again immediately after use, opened tubes should be used up as quickly as possible. Processing Presspack Remove tamper-evident seal. Regulate discharge by smooth turning of the cap from min. to max. Press the lever and process the medium. After having turned the cap into the “min.” position the valve closes automatically and the product flow is stopped. Joining the components In order to guarantee an ideal wetting, the bonding parts need to be joined, before the adhesive skins over (skin-over time).

## Storage

When unopened and stored in normal climate (+23°C and 50 % rel. air humidity), WEICON Elastic Adhesives and Sealants have a shelf life of 12 months.

## Safety and health

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

## Accessories

- 13955031 V-Joint Nozzle, 1 PCE
- 13250009 Compressed Air Cartridge Gun, 1 PCE
- 13250002 Cartridge Gun Special, 1 PCE
- 13250001 Cartridge Gun, 1 PCE

## Available sizes:

- 13051200 Black-Seal Special Silicone, 200 ml, black
- 13051310 Black-Seal Special Silicone, 310 ml, black
- 13051085 Black-Seal Special Silicone, 85 ml, black

To the product detail page:



### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871 info@weicon.it

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr