

# GMK 2410 Contact Adhesive



permanently elastic | moisture-resistant

WEICON GMK 2410 is an adhesive based on polychloroprene (CR) for the high-strength, full-surface and flexible bonding of: - rubber to rubber - rubber to metal GMK 2410 also bonds cellular rubber, PE foam, leather, felt, insulating material, textiles, wood, and many plastics. WEICON GMK 2410 is not suitable for materials such as expanded polystyrene, polyethylene, polypropylene, flexible PVC foam, and artificial PVC leather.

## Technische Daten

|                                 |                             |
|---------------------------------|-----------------------------|
| Base                            | Polychloroprene (CR)        |
| Colour                          | brown                       |
| Density                         | 0,93 g/cm <sup>3</sup>      |
| Evaporation time                | 5 - 10 min.                 |
| Consumption                     | 250 - 300 g/cm <sup>2</sup> |
| Contact bonding time            | 10 min.                     |
| Final strength (100 % strength) | 24 h                        |
| Processing temperature          | +15 to +35                  |
| Shelf life                      | 12 mon.                     |
| Temperature resistance          | -40 to +80                  |
| IMPA Code                       | 815237/38                   |

## Surface pre-treatment

The parts to be joined must be clean, dry, and free of dust and grease (WEICON Surface Cleaner). Roughening the surfaces effectively increases the strength of the bond.

## Processing

Stir the product well before use and then evenly apply a thin layer over the entire surface to be bonded with a paint brush or spatula (smooth or fine-toothed). Two or three thin layers may be required depending on the type of material and application. Depending on the layer thickness, ambient temperature and air humidity, allow the coated surfaces to evaporate for 5 - 10 minutes. With absorbent surfaces (e.g. felt), an additional adhesive layer should be applied after evaporating. As soon as the surfaces are dry but still feel a bit sticky (finger test), the parts must be joined under brief, strong pressure (e.g. with a roller or hammer). If the evaporation time is exceeded (over-drying), the adhesive must be applied again. Non-cured, exceeding adhesive can be removed with WEICON Surface Cleaner.

## Storage

Shelf life, when stored in tightly closed container in a dry place at room temperature (+15°C to +25°C). 12 months when unopened

## Safety and health

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Accessories

|          |                       |
|----------|-----------------------|
| 10953001 | Processing spatula    |
| 10953003 | Processing spatula    |
| 10953020 | Contour Spatula Flexy |

## Available sizes:

|          |   |
|----------|---|
| 16100700 | GMK 2410 Contact Adhesive, 0,7 kg, brown  |
| 16100925 | GMK 2410 Contact Adhesive, 25 kg, brown   |
| 16100300 | GMK 2410 Contact Adhesive, 0,3 kg, brown  |
| 16100185 | GMK 2410 Contact Adhesive, 185 g, brown   |
| 16100350 | GMK 2410 Contact Adhesive, 0,35 kg, brown |
| 16100905 | GMK 2410 Contact Adhesive, 5 kg, brown    |

To the product detail page:



## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 [info@weicon.ae](mailto:info@weicon.ae)

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 [info@weicon.cz](mailto:info@weicon.cz)

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 [info@weicon.de](mailto:info@weicon.de)

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 [office@weicon.com](mailto:office@weicon.com)

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 [info@weicon.com.sg](mailto:info@weicon.com.sg)

WEICON Inc. Canada phone +1 877 620 8889 [info@weicon.ca](mailto:info@weicon.ca)

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 [info@weicon.es](mailto:info@weicon.es)

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871 [info@weicon.it](mailto:info@weicon.it)

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 [info@weicon.co.za](mailto:info@weicon.co.za)

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 [info@weicon.com.tr](mailto:info@weicon.com.tr)