



ADHESIVES & SEALANTS



Weiconlock AN 301-72 Flange Sealing Adhesive

Weiconlock AN 301-72 is a high quality grade of anaerobic adhesive designed for pipe and flange sealing applications. When used in these situations, Weiconlock Anaerobic Adhesives exhibit excellent chemical resistance, high elasticity, ease of use and completely fill flange face voids to ensure face-to-face contact.

AN 301-72 is white in colour and contains PTFE for additional sealing performance. It is non-marking, high temperature resistant and approved by NSF for food applications and DVGW for gas sealing.

Properties

Colour	White
For Threaded Joints Up To	M 80
Viscosity at 25°C Brookfield	15,000 – 60,000 MPa
Gap Filling Capacity (Max.)	0.3 mm
Breakaway Strength (Thread)	5 – 10 Nm
Prevailing Strength (Thread)	4 – 6 Nm
Shear Strength (DIN 54452)	5 – 7 N/mm ²
Handling Strength At Room Temperature	15 - 30 Minutes
Final Strength At Room Temperature	6 - 12 Hours
Temperature Resistance	-60°C to +200°C

Approvals & Recognitions


NSF for Food Applications

DVGW for Gas Sealing


Weiconlock Adhesives General Information

All grades of Weiconlock are high quality anaerobic adhesives based on specialised methacrylate resins. While the grades differ in cure time, temperature resistance, cure strength, colour, viscosity and more; one thing that unites them is the fact that they only cure when in contact with metal and deprived of air. This special feature allows Weiconlock adhesives to be very easy to use as there's essentially no pot life.

As liquid adhesives, Weiconlock adhesives completely fill any gaps and thus protect against leakage and fretting corrosion. Once cured, these high quality adhesives form a shock and vibration resistant joint with excellent resistance to chemicals and solvents.



General Curing Speed of Weiconlock
Depending on Material



Compression Shear Strength of Weiconlock
Depending on the Metal (DIN 544521)

Visit: www.agaus.com.au

Phone: 1300 098 060

Important

This information should not be treated as a substitute for specific technical advice. AG does not offer such advice and cannot warrant the performance or suitability of products for particular applications.

Weiconlock AN 301-72 Flange Sealing Adhesive

Weiconlock General Chemical Resistance Table

Acetaldehyde	+	Ethylene Dichloride	+	Perchloroethylene (Dry)	+
Acetate Solvent	+	Ethylene Glycol	+	Perchloric Acid (10%)	%+
Acetic Acid (10%)	%+	Fatty Acids	+	Permanganic	-
Acetic Acid (80%)	%O	Ferrous Sulphate	+	Peroxide Bleaching	+
Acetone	+	Formaldehyde (Cold)	+	Peroxy	-
Alcohols	+	Formic Acid (Cold)	+	Persulphuric (10%)	%+
Alkaline Solution	+	Freon	+	Phenol	+
Ammoniac Anhydride	-	Fuel Oil	+	Phenolic Resins	+
Ammonium Hydroxide	O	Fuming Nitric Acid	-	Phosphoric Acid 10% Hot	O
Amyl Acetate	+	Fuming Sulphuric Acid	-	Phosphoric Acid 10% Cold	+
Aniline	+	Gasoline	+	Phosphoric Acid 50% Hot	O
Aromatic Gasoline	+	Glycolic Acid	+	Phosphoric Acid 50% Cold	O
Aromatic Solvent	+	Glycerine	+	Phosphoric Acid 85% Hot	-
Ash Slurry	+	Grease Lubrication	+	Phosphoric Acid 85% Cold	O
Barium Sulphate	+	Hydrogen Bromide (10%)	%+	Phthalic	+
Battery Acid (10%)	%+	Hydrocyanic Acid (10%)	%+	Potash Alum	+
Benzene	+	Hydrogen	+	Potassium Acetate	+
Benzoic Acid	+	Hydrogen Peroxide	O	Potassium Hydroxide	-
Boric Acid	+	Concentrate	O	Pyridine	+
Brake Fluid	+	Hydrofluoric Acid	-	River Water	+
Butadiene	+	Heptane	+	Sewage	+
Butyric (10%)	%+	Hydrazine	+	Sea Water	+
Butylaldehyde	+	Hydrochloric Acid	O	Silicone Oils	+
Butylamine	+	Isocyanate Resin	+	Sorbitol	+
Butyl Acetate	+	Isooctane	+	Steam Sterilisation	+
Butyl Chloride	+	Ketones	+	Styrene	+
Cadmium Sulphate	+	Lithium Chloride	+	Sulfones	+
Castor Oil	+	Maleic	+	Sulfonic Acids (10%)	%+
Cellulose Acetate	+	Melamine Resin	+	Sulphuric Acid (75-100%)	%-
Chinon	+	Mercaptan, Thioalcohol	+	Sulphur Mud Solution in	+
Chlorine (Dry)	-	Methane	+	Carbon Disulphide	+
Chlorine Alcohol	+	Methylamine	+	Sulphurous Acid	O
Chloramine	+	Methyl Ethyl Ketone	+	Sulphuric Acid (75%)	%O
Chlorine Dioxide	O	Methyl Acetate	+	Turpentine	+
Chlorinated Hydrocarbon	+	Mineral Oil, White	+	Thiourea	+
Chloroform (Dry)	+	Mine Water	+	Toulene, Methylbenzene	+
Coal Tar	+	Naphtha, Petroleum	+	Trichloroethane	+
Copper Chloride	+	Naphthalene	+	Trichloromethane	+
Copper Sulphate	+	Natronhydroxyd 20% hot	%O	Trioxane	+
Cold Salt Water	+	Natronhydroxyd 20% cold	%+	Vapor Pressure (Low)	+
Developer Liquid	+	Natronhydroxyd 50% hot	%-	Vaseline	+
Dichloroethylether	+	Natronhydroxyd 50% cold	%O	Vinyl Acetate	+
Diethyl ether	+	Natronhydroxyd 70% hot	%-	Wax	+
Diglycollic	+	Natronhydroxyd 70% cold	%O	Xylene, Dimethylbenzene	+
Dioxane (Dry)	+	Nitric Acid (20%)	%+		
Emulsified Oils	+	Oils	+		
Ethyl Acetate	+	Oxalic Acid	+		
Ethylenediamine	+	Paraffin Oil, Kerosene	+		

+ = Good Resistance

O = Preliminary Tests or Resistance Tests are Recommended

% = Weiconlock adhesives are resistant only up to the indicated concentration

- = Weiconlock adhesives are not suitable, or may be used only after thorough preliminary tests

Visit: www.agaus.com.au

Phone: 1300 098 060

Important

This information should not be treated as a substitute for specific technical advice. AG does not offer such advice and cannot warrant the performance or suitability of products for particular applications.



ADHESIVES & SEALANTS



Weiconlock AN 301-72 Flange Sealing Adhesive

Preparation of the Surface

In general, Weiconlock adhesives do not require special surface pre-treatment as slightly oil surfaces (e.g. on 'as received' parts) will be tolerated. However, best results will be achieved if Weiconlock is used on parts that are cleaned and degreased (Cleaner S may be ideal). If required, the parts should be slightly roughened.

Application

Weiconlock AN 301-72 is ready for use and should be applied evenly directly from the bottle/tube with the dispensing tip (avoid direct contact of tip with metal). On press fitted parts and larger cylindrical assemblies a thin uniform layer should be applied to both surfaces. In the case of blind threaded holes, dispense a sufficient quantity into the bore hole. On screws and bolts, apply AN 301-72 around the thread.

Do not pour any Weiconlock fluid that has had contact with metal back into the bottle. Even the smallest metal particles will cause the content of the bottle to cure. In series construction, the use of manual or automatic applicators is possible.

Physiological properties / health and safety at work

Weiconlock adhesives generally do not cause allergic reactions to the skin. However, in isolated cases where skin is continuously bruised or micro-lacerated sensitisation may occur. Therefore, extensive and direct contact with the skin should be avoided (e.g. by the use of Weicon Hand Protective Foam). For more information on this topic, please refer to the appropriate SDS.

Weiconlock Activator F

The cure time of all grades of Weiconlock adhesives can be reduced by pre-treating surfaces with Weiconlock Activator F which is recommended for all passive surfaces (such as high alloyed steel, chromate layers, plastics, ceramics, aluminium, zinc or nickel) and which is indispensable when working in low temperature (+10°C and below) environments or when covering large gaps. On non-metallic surfaces, Weiconlock AN 301-72 is made effective by the activator.

Cure

Weiconlock remains liquid as long as it is in contact with the air. Curing starts when Weiconlock is in contact with metal and deprived of air. Observable cure time is influenced not only by the type of Weiconlock, but also the material(s) it is exposed to and the environmental temperature.

Dismantling

Weiconlock AN 301-72 cures with medium strength. Bonds formed with this anaerobic adhesive will be able to be disassembled using normal tools when it is required.

Storage

Weiconlock AN 301-72 can be stored in its unopened original container for at least 12 months at room temperature. Keep away from heat sources and direct sunlight.

Availability

Weiconlock AN 301-72 is available in 50ml Pens and 200ml bottles.

Visit: www.agaus.com.au

Phone: 1300 098 060

Important

This information should not be treated as a substitute for specific technical advice. AG does not offer such advice and cannot warrant the performance or suitability of products for particular applications.